



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Melanie KLASSEN-MEMMER et al.

Confirmation No.: 2849

Serial No.: 10/022,523

Examiner: Shean Chiu Wu

Filed: December 20, 2001

Group Art Unit: 1756

Title: LIQUID-CRYSTAL MEDIUM, AND ELECTRO-OPTICAL DISPLAY
CONTAINING SAME

SUBMISSION OF ENGLISH TRANSLATION


Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

Applicants attach herewith a verified English translation of German language text filed under No. 100 63 943.7 on December 20, 2000.

The Commissioner is hereby authorized to charge any fees associated with this response or credit any overpayment to Deposit Account No. 13-3402.

Respectfully submitted,



John A. Sopp, Reg. No. 33,103
Attorney/Agent for Applicants

MILLEN, WHITE, ZELANO
& BRANIGAN, P.C.
Arlington Courthouse Plaza 1
2200 Clarendon Blvd. Suite 1400
Arlington, Virginia 22201
Telephone: (703) 243-6333
Facsimile: (703) 243-6410

Attorney Docket No.: MERCK-2331

Date: June 18, 2004


IN THE US PATENT AND TRADEMARK OFFICE

In the matter of an application for a German Patent in the name of Merck Patent GmbH, filed under No. 100 63 943.7 on 20 December 2000, and in the matter of an application for a US Patent.

I, Dr. Ashwood Stephen DRANE, B.Sc., Ph.D., BDÜ, translator to Steve Drane Translations Ltd. of Beechwood, Chivery, Tring, Hertfordshire, England, do solemnly and sincerely declare:

1. That I am a citizen of the United Kingdom of Great Britain and Northern Ireland.
2. That I am well acquainted with the German and English languages and am a competent translator thereof.
3. That the following is to the best of my knowledge and belief a true and correct translation of the above-referenced patent application and the Official Certificate attached thereto

Dated this 21st day of May 2004



Dr. Ashwood Stephen Drane

FEDERAL REPUBLIC OF GERMANY



Priority certificate regarding the filing of a patent application

File reference: 100 63 943.7

Date of filing: 20 December 2000

Applicant/proprietor: Merck Patent GmbH, Darmstadt/DE

Title: Liquid-crystal medium, and electro-optical display
containing same

IPC: C 09 K, G 02 F, G 09 F

**The attached pages are a correct and accurate reproduction of the original
documents of this patent application.**

Seal

Munich, 17 July 2001
German Patent and Trademark Office
On behalf of
The President

[signature]

Agurks

**Merck Patent Gesellschaft
mit beschränkter Haftung
64271 Darmstadt**

**Liquid-crystal medium, and electro-optical
display containing same**

**Liquid-crystal medium,
and electro-optical display containing same**

5 The present invention relates to liquid-crystal displays, particularly active matrix addressed liquid-crystal displays (AMDs or AMLCDs), especially those which use an active matrix comprising thin film transistors (TFTs) or varistors. In addition, the present application relates to liquid-crystal media for use in displays of this type. AMDs of this type are able to use various active electronic switching elements. The most widespread are displays
10 which use three-pole switching elements. These are also preferred in the present invention. Examples of three-pole switching elements of this type are MOS (metal oxide silicon) transistors or the above-mentioned TFTs or varistors. In the TFTs, various semiconductor materials, predominantly silicon or alternatively cadmium selenide, are used. In particular, poly-
15 crystalline silicon or amorphous silicon is used. In contrast to the three-pole electronic switching elements, matrixes of 2-pole switching elements, such as, for example, MIM (metal insulator metal) diodes, ring diodes or "back to back" diodes, can also be employed in AMDs. However, as also explained in greater detail below, these are generally not preferred owing to the worse electro-optical properties achieved by the AMDs.
20

The liquid crystals used as dielectrics in liquid-crystal displays of this type are those whose optical properties change reversibly on application of an electric voltage. Electro-optical displays which use liquid crystals as media
25 are known to the person skilled in the art. These liquid-crystal displays use various electro-optical effects.

The most widespread conventional displays use the TN effect (twisted nematic, having a nematic structure which is twisted by about 90°), the
30 STN (supertwisted nematic) effect or the SBE effect (supertwisted birefringence effect). In these and similar electro-optical effects, liquid-crystalline media of positive dielectric anisotropy ($\Delta\epsilon$) are used.

Since the operating voltage in displays in general, i.e. including in displays
35 using these effects, should be as low as possible, use is made of liquid-crystal media of large dielectric anisotropy, which are generally composed

predominantly of dielectrically positive liquid-crystal compounds and at most comprise relatively small/low proportions of dielectrically neutral compounds.

5 In contrast to the said conventional displays utilising the said electro-optical effects which require liquid-crystal media of positive dielectric anisotropy, there are other electro-optical effects which use liquid-crystal media of negative dielectric anisotropy, such as, for example, the ECB (electri-
10 cally controlled birefringence) effect and its sub-forms DAP (deformation of aligned phases), VAN (vertically aligned nematics) and CSH (colour super homeotropics). These are the subject-matter of the present application.

The IPS (in plane switching) effect, which has been employed to an increased extent recently, can use both dielectrically positive and dielectrically negative liquid-crystal media, similarly to "guest/host" displays, which
15 can employ dyes either in dielectrically positive or in dielectrically negative media, depending on the display mode used. In the case of the liquid-crystal displays mentioned in this paragraph, those which use dielectrically negative liquid-crystal media are also the subject-matter of the present
20 application.

A further highly promising type of liquid-crystal display are so-called "axi-
25 ally symmetric microdomain" (abbreviated to ASM) displays, which are preferably addressed by means of plasma arrays (plasma addressed liquid cystal displays, or PA LCDs). These displays are also the subject-matter of the present application.

The liquid-crystal media employed in the above-mentioned liquid-crystal displays and all liquid-crystal displays which utilise similar effects generally consist predominantly and in most cases even very substantially of
30 liquid-crystal compounds having the corresponding dielectric anisotropy, i.e. of compounds of positive dielectric anisotropy in the case of dielectrically positive media and of compounds of negative dielectric anisotropy in the case of dielectrically negative media.

35

5 In the media used in accordance with the present application, at most significant amounts of dielectrically neutral liquid-crystal compounds and in general only very small amounts or even no dielectrically positive compounds at all are typically employed, since in general the liquid-crystal displays should have the lowest possible addressing voltages. For this reason, liquid-crystal compounds having the opposite sign of the dielectric anisotropy to the dielectric anisotropy of the medium are generally employed extremely sparingly or not at all.

10 The liquid-crystal media of the prior art have relatively low low-temperature stabilities. Thus, the nematic phases often extend only down to -20°C and in some cases even only down to -10°C . In addition, the threshold voltages (V_0) are at the same time relatively high, in most cases even greater than 2 V.

15 For the most part, the liquid-crystal media of the prior art have relatively unfavourable values for Δn , which are often much reater than 0.10. However, such large Δn values are not particularly advantageous for VAN displays, since small values for the optical retardation are typically used in
20 VAN displays. Thus, for example, a $d \cdot \Delta n$ of approximately $0.30 \mu\text{m}$ is employed in the case of an untwisted director orientation or a $d \cdot \Delta n$ of approximately $0.40 \mu\text{m}$ is employed with a 90° twist. Such large Δn values require the realisation of very small layer thicknesses, which, although favourable for the response times observed, result, however, in low production yields.

25 In most cases, the most favourable Δn values for practical displays are in the range from 0.07 to 0.12. This also applies to IPS displays.


30 In addition, the response time of the prior-art displays is often inadequately long, in particular for video-capable displays. Thus, the viscosities of the liquid-crystal media must be improved, i.e. reduced. This applies in particular to the rotational viscosity and very particularly at low temperatures. A reduction in the flow viscosity generally results, in particular in the case of
35 displays having a homeotropic edge alignment of the liquid crystals (for

example in ECB and VAN displays), in a shortening of the filling times during production of the displays.


Thus, there has been and continues to be a great demand for liquid-crystal media which do not have the disadvantages of the media from the prior art or at least do so to a significantly reduced extent.

Surprisingly, it has been found that this is achieved by the liquid-crystal media according to the invention. These media comprise

- a) a dielectrically negative, liquid-crystalline component (component A) which comprises one or more dielectrically negative compound(s) of the formula I




in which



preferably,

independently of one another, are



particularly preferably



R^{11} is alkyl having from 1 to 7 carbon atoms, preferably n-alkyl, particularly preferably n-alkyl having from 1

to 5 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy, particularly preferably n-alkoxy having from 1 to 5 carbon atoms, or alkoxy-alkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, preferably alkenyloxy,



R^{12} is alkyl or alkoxy having from 1 to 7 carbon atoms, preferably alkoxy, preferably n-alkoxy and particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, preferably alkenyloxy,

one of Z^{11} and Z^{12} is OCF_2 or CF_2O and the other is a single bond, and

n is 0 or 1,

and

- b) a dielectrically negative, liquid-crystalline component (component B) which preferably comprises one or more dielectrically negative compound(s) selected from the group consisting of the compounds of the formulae II and III





in which


R^{21} is alkyl having from 1 to 7 carbon atoms, preferably n-alkyl and particularly preferably n-alkyl having from 1 to 5 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy and particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, preferably alkenyloxy,

R^{22} is alkyl having from 1 to 7 carbon atoms, preferably n-alkyl, particularly preferably n-alkyl having from 1 to 3 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy, particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms,


Z^{21} and Z^{22} are each, independently of one another, $-\text{CH}_2\text{-CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{COO}-$ or a single bond, preferably $-\text{CH}_2\text{-CH}_2-$ or a single bond and particularly preferably a single bond,




are each, independently of one another, ,






preferably





5 L^{21} and L^{22} are both C-F or one of the two is N and the other is C-F, preferably both are C-F, and

m is 0 or 1,



15

respectively in the case of the formula II,


20 Z^3 is $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{COO}-$ or a single bond, preferably $-\text{CH}_2-\text{CH}_2-$ or a single bond and particularly preferably a single bond,

25 R^{31} and R^{32} are each, independently of one another, alkyl having from 1 to 7 carbon atoms, preferably n-alkyl and particularly preferably n-alkyl having from 1 to 5 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy and particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, and

30 l is 1 or 2,

35 and optionally



- c) a dielectrically neutral component (component C) which comprises one or more dielectrically neutral compound(s) of the formula IV




in which

10 R^{41} and R^{42} are each, independently of one another, as defined above for R^{21} in the case of the formula II,

15 Z^{41} , Z^{42} and Z^{43} are each, independently of one another, $-\text{CH}_2\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{COO}-$ or a single bond,



are each, independently of one another, ,




o and p , independently of one another, are 0 or 1,

but preferably


35

R^{41} and R^{42} are each, independently of one another, alkyl or alkoxy having 1-5 carbon atoms or alkenyl having 2-5 carbon atoms,


5




10




and



are each, independently of one another,




15



and very particularly preferably at least two of these rings are


20




where two adjacent rings are very particularly preferably linked

25

directly, preferably



or




30

and optionally

d) one or more dielectrically positive compound(s) of the formula V



35




in which

R^5 is alkyl or alkoxy having from 1 to 7 carbon atoms, or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms,



Z^{51} , Z^{52} and Z^{53} are each, independently of one another, $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{COO}-$ or a single bond,



and



are each, independently of one another,




X^5 is F, OCF_2H or OCF_3 , and

Y^5 is H or F, preferably F in the case where $X = \text{F}$ or OCF_2H , and

q and r are each, independently of one another, 0 or 1.

In a further preferred embodiment, the medium comprises one or more dielectrically negative compounds of the formula VI



VI

5

in which

10

R^{61} and R^{62} are alkyl having from 1 to 7 carbon atoms, preferably n-alkyl and particularly preferably n-alkyl having from 1 to 5 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy and particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, very particularly preferably both are n-alkoxy having from 1 to 5 carbon atoms,

15

Z^6 is as defined above for Z^{21} in the case of the formula II,

20


L^{61} and L^{62} are both C-F or one of the two is N and the other is C-F, and

L^{63} and L^{64} are both C-F or one of the two is N and the other is C-F.

25

In a further preferred embodiment, the medium comprises one or more dielectrically negative compounds of the formula VII

30



VII

in which





35




R^{71} and R^{72} are alkyl having from 1 to 7 carbon atoms, preferably n-alkyl and particularly preferably n-alkyl having from

1 to 5 carbon atoms, alkoxy having from 1 to 7 carbon atoms, preferably n-alkoxy and particularly preferably n-alkoxy having from 2 to 5 carbon atoms, or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms, very particularly preferably both are n-alkoxy having from 1 to 5 carbon atoms, and

L^{71} and L^{72} are both C-F or one of the two is N and the other is C-F.

Component A preferably consists predominantly, particularly preferably consists essentially completely and very particularly preferably consists virtually completely, of one or more compounds of the formula I. These compounds of the formula I are preferably selected from the group consisting of the compounds of the formulae I-1 to I-8












in which

R^{11} , R^{12} and Z^{12} are each as defined above under the formula I.

The compounds of the formula I are particularly preferably selected from the group consisting of the compounds of the following sixteen formulae I-1a to I-8b







in which

R^{11} and R^{12} are as defined above under the formula I, and R^{11} is preferably alkyl having from 1 to 7 carbon atoms or alkenyl having from 2 to 7 carbon atoms, and R^{12} is preferably alkoxy having from 1 to 7 carbon atoms or alkenyloxy having from 2 to 7 carbon atoms.

The compounds are very particularly preferably selected from the group consisting of the compounds of the formulae I-1a, I-1b, I-2a, I-3a, I-4a, I-4b, I-5a, I-6a, I-6b and I-7a and in particular from the group consisting of the compounds of the formulae I-1b and I-7a.

In the present application, in connection with the quoting of the constituents of the compositions:

- comprise means that the concentration of the relevant constituents in the composition is preferably 10% or more, particularly preferably 20% or more,
- consist predominantly of means that the concentration of the relevant constituents in the composition is preferably 50% or more, particularly preferably 55% or more and very particularly preferably 60% or more,
- consist essentially completely of means that the concentration of the relevant constituents in the composition is preferably 80% or more, particularly preferably 90% or more and very particularly preferably 95% or more, and
- consist virtually completely of means that the concentration of the relevant constituents in the composition is preferably 98% or more, par-



particularly preferably 99% or more and very particularly preferably 100.0%.

This applies both to the media as compositions with their constituents, which may be components and compounds, and to the components with their constituents, those of the compounds.

The liquid-crystal media preferably comprise one or more compounds selected from the group consisting of the compounds of the formulae I-1, I-2 and I-4, particularly preferably of the formulae I-2 and/or I-4.

Component B preferably consists predominantly, particularly preferably consists essentially completely and very particularly preferably consists virtually completely, of one or more compounds selected from the group consisting of the compounds of the formulae II and III.

The compounds of the formula II are preferably selected from the group consisting of the compounds of the formulae II-1 and II-3



in which


R^{21} and R^{22} are as defined above under the formula I, and preferably

R^{21} is n-alkyl having from 1 to 7 carbon atoms, n-alkoxy having from 1 to 7 carbon atoms or alkenyloxy having from 2 to 7 carbon atoms,

5 R^{22} is n-alkoxy having from 1 to 7 carbon atoms or alkenyloxy having from 2 to 7 carbon atoms,
and in the formulae I2 and I3 is alternatively n-alkyl having from 1 to 7 carbon atoms,


in which

10




preferably

15



n is 0 or 1.






20 The compounds of the formula III are preferably selected from the group consisting of the compounds of the formulae III-1 and III-2



in which


30 R^{31} and R^{32} are as defined above under the formula III and are preferably n-alkyl.



35 The liquid-crystal media particularly preferably comprise one or more compounds selected from the group consisting of the compounds of the formulae II-1a to II-1f



in which R^{21} and R^{22} are as defined above in the case of the formula II and are preferably as defined above in the case of the formula II-1.


The liquid-crystal media particularly preferably comprise one or more compounds selected from the group consisting of the compounds of the formulae II-2a to II-2c






in which R^{21} and R^{22} are as defined above in the case of the formula II and are preferably as defined above in the case of the formula II-2.


15 The liquid-crystal media particularly preferably comprise one or more compounds of the formula II-3a



in which R^{21} and R^{22} are as defined above in the case of the formula II and are preferably as defined above in the case of the formula II-3.





25 Component C preferably consists predominantly, particularly preferably consists essentially completely and very particularly preferably consists virtually completely, of one or more compounds of the formula IV. These compounds of the formula IV are preferably selected from the group consisting of the compounds of the formulae IV-1 to IV-3






5 in which R^{41} , R^{42} , Z^{41} , Z^{42} , $\text{C}_6\text{H}_4(A^{42})$ and $\text{C}_6\text{H}_4(A^{43})$ are each as correspondingly defined above in the case of the formula IV.


10 The liquid-crystal medium especially preferably comprises one or more compounds selected from the group consisting of the compounds of the formulae IV-1a to IV-1d, IV-1e, IV-2a to IV-2e and IV-3a to IV-3c



25 in which n and m are each, independently of one another, from 1 to 5, and o and p are each, independently thereof and one another, from 0 to 3,








35



in which R^{41} and R^{42} are each as defined above under the formula IV1, and the phenyl rings may optionally be fluorinated, but not in such a way that the compounds are identical with those of the formula II and its sub-formulae. R^{41} is preferably n-alkyl having from 1 to 5 carbon atoms, especially preferably having from 1 to 3 carbon atoms, and R^{42} is preferably n-alkyl or n-alkoxy having from 1 to 5 carbon atoms or alkenyl having from 2 to 5 carbon atoms. Of these, particular preference is given to compounds of the formulae IV1a to IV1d.

Component D preferably consists predominantly, particularly preferably consists essentially completely and very particularly preferably consists virtually completely, of one or more compounds of the formula IV. These compounds of the formula IV are preferably selected from the group consisting of the compounds of the formulae V-1 to V-4



in which R^5 , Z^{52} , Z^{53} and  are as defined above for the

formula I, but preferably


5

R^5 is alkyl having 1-7 carbon atoms or alkenyl having 2-7 carbon atoms, preferably vinyl or 1E alkenyl,

one of

10 Z^{52} and Z^{53} is a single bond and the other is $-\text{CH}_2\text{CH}_2-$, $-\text{COO}-$ or a single bond, and

15



In a preferred embodiment, the medium comprises one or more compounds of the formula VI, preferably selected from the group consisting of the compounds of the formulae VI-1 to VI-4

20



25



30




35



in which R^{61} and R^{62} are as defined above in the case of the formula VI.

In a preferred embodiment, the medium comprises one or more compounds of the formula VII, preferably from the group consisting of the formula VII-1



10 in which

R^{71} and R^{72} are as defined above in the case of the formula VII.

15 In a preferred embodiment, the liquid-crystal media according to the invention comprise in total, based on the mixture as a whole,

from 5% to 85%, preferably from 10% to 55% and particularly preferably from 15% to 40%, of component A, preferably of compounds of the formula I,

20 from 5% to 85%, preferably from 10% to 85%, particularly preferably from 20% to 80% and very particularly preferably from 40% to 75%, of component B, preferably of compounds of the formulae II and III, where the ratio of the concentrations of compounds II and III is preferably greater than or equal to 2:1, particularly preferably greater than or equal to 3:1 and very particularly preferably greater than or equal to 4:1,

25 from 0% to 50%, preferably from 0% to 40%, particularly preferably from 0% to 30% and very particularly preferably from 5% to 25%, of component C, preferably of compounds of the formula IV, and

30 from 0% to 40%, preferably from 0% to 30%, particularly preferably from 0% to 20% and very particularly preferably from 1% to 15%, of component D, preferably of compounds of the formula IV.

35

Here, as throughout the present application, the term compounds, also written as compound(s), means both one and a plurality of compounds, unless explicitly stated otherwise.

5 The individual compounds are employed here in concentrations of in each case from 1% to 30%, preferably from 2% to 30% and particularly preferably from 4% to 16%. An exception is formed here by compounds having three phenyl rings and compounds having four six-membered rings. These compounds are employed in concentrations of in each case from 0.5% to 10 15%, preferably from 1% to 10% and particularly preferably from 1% to 8%, per individual compound. In the case of the compounds of the formula I in which $n = 0$, the preferred limits to the concentrations for the proportion of the individual compounds in the medium are from 1% to 20%, preferably from 2% to 15% and particularly preferably from 5% to 8%. In the case of 15 the compounds of the formula I in which $n = 1$, the preferred limits to the concentrations for the proportion of the individual compounds in the medium are from 1% to 30%, preferably from 2% to 20% and particularly preferably from 8% to 12%.

20 In a preferred embodiment, the liquid-crystal media especially preferably comprise in total

from 10% to 40% of compounds of the formula I,
from 50% to 90% of compounds of the formulae II and III,
25 from 0% to 40% of compounds of the formula IV, and
from 0% to 20% of compounds of the formula V.

In this embodiment, the liquid-crystal media very particularly preferably comprise in total

30 from 15% to 35% of compounds of the formula I,
from 60% to 80% of compounds of the formula II and III,
from 0% to 20% of compounds of the formula IV, and
from 0% to 5% of compounds of the formula V.

35

In a particularly preferred embodiment, which may be identical and preferably is identical with the preferred embodiments described above for the preferred concentration ranges, the liquid-crystal media comprise:

- 5 • one or more compounds of the formula I, preferably selected from the group consisting of the compounds of the formulae I-1b and I-7a, preferably in which R¹¹ is n-alkyl and R¹² is alkoxy, and
- one or more compounds of the formula II-1, preferably
- 10 - one or more compounds of the formula II-1a, and/or, preferably and,
- one or more compounds of the formula II-1c, and/or, preferably and,
- one or more compounds of the formulae III-1, and/or, preferably and,
- 15 • one or more compounds selected from the group consisting of the compounds of the formulae IV-1 to IV-4, preferably
- one or more compounds formula IV-1 selected from the group consisting of the compounds of the formulae IV-1a to IV-1d, very particularly preferably selected from the group consisting of the
- 20 formulae V-1c and IV-1d and in particular of the formula IV-1c, and/or, preferably and,
- one or more compounds of the formula IV-2c and/or IV-2e, and/or, preferably and,
- 25 - one or more compounds of the formula IV-3c and/or IV-3d, and/or, preferably and,
- one or more compounds of the formula IV4, and/or
- one or more compounds selected from the group consisting of the compounds of the formulae V to VII.
- 30

Particular preference is given here to liquid-crystal media which comprise

- 35 - one or more compounds of the formula I, preferably selected from the group consisting of the compounds of the formulae I-1b and I-7a, prefer-

ably in which R^{11} is n-alkyl and R^{12} is alkoxy, and in particular in each case in concentrations of from 6% to 20% per compound, and/or

- 5 - one or more compounds of the formula II-1a, in particular in each case in concentrations of from 4% to 18% per compound, and/or
- 10 - one or more compounds of the formula II-1c, in particular in each case in concentrations of from 3% to 15% per compound, preferably in each case one or more compounds in which R^{21} is alkyl having from 1 to 3 carbon atoms and R^{22} is alkoxy having from 1 to 3 carbon atoms, and in which R^{23} is alkyl having from 1 to 3 carbon atoms and R^{32} is alkyl having from 1 to 3 carbon atoms, and/or
- 15 - one or more compounds of the formulae IV1, preferably of the formulae IV-1b and/or IV-1c.

These media may, if desired, comprise one or more compounds selected from the group consisting of the compounds of the formulae V-1 to V-4.

- 20 The liquid-crystal media according to the invention preferably have nematic phases of in each case at least from -20°C to 70°C , particularly preferably from -30°C to 80°C , very particularly preferably from -40°C to 80°C and most preferably from -40°C to 105°C .

- 25 The term "have a nematic phase" here means firstly that no smectic phase and no crystallisation is observed at low temperatures at the corresponding temperature and secondly also that no clearing occurs on heating from the nematic phase. The investigation at low temperatures is carried out in a flow viscometer at the corresponding temperature and checked by storage for at least 100 hours in test cells having a layer thickness corresponding to the electro-optical application. At high temperatures, the clearing point is measured in capillaries by conventional methods.
- 30

- 35 Furthermore, the liquid-crystal media according to the invention are characterised by relatively low optical anisotropy values. The birefringence values are preferably in the range from 0.060 to 0.150, particularly prefer-

ably in the range from 0.070 to 0.120 and very particularly preferably in the range from 0.070 to 0.110.


5 In addition, the liquid-crystal media according to the invention have low values for the threshold voltage (V_0) of less than or equal to 2.2 V, preferably less than or equal to 2.0 V, particularly preferably less than or equal to 1.9 V and very particularly preferably less than or equal to 1.85 V. In a particularly preferred embodiment, the liquid-crystal media according to the invention have values for the threshold voltage which are less than or
10 equal to 1.5 V.

These preferred values for the individual physical properties are also observed in each case in combination with one another.

15 Independently of the above-mentioned dimensioning limits for the compounds of the formulae I, II and III, compounds of the formulae I and II are employed in the liquid-crystal media in accordance with the present application in a concentration of up to about 25% per individual substance, and compounds of the formula III are employed in a concentration of up to
20 about 20%, preferably up to 16%, per individual substance. Compounds of the formula I-1 are preferably employed in concentrations of up to about 20%, preferably up to 15%, per individual substance.

25 In the present application, " \leq " means less than or equal to, preferably less than, and " \geq " means greater than or equal to, preferably greater than.

In the present application,



30 denote trans-1,4-cyclohexylene.

In the present application, the term dielectrically positive compounds means compounds having a $\Delta\epsilon > 1.5$, dielectrically neutral compounds means those in which $-1.5 \leq \Delta\epsilon \leq 1.5$, and dielectrically negative compounds means those having $\Delta\epsilon < -1.5$. The dielectric anisotropy of the
35 compounds is determined here by dissolving 10% of the compounds in a

liquid-crystalline host and determining the capacitance of this mixture at 1 kHz in at least one test cell having a thickness of 20 μm with a homeotropic surface alignment and in at least one test cell having a thickness of 20 μm with a homogeneous surface alignment. The measurement voltage is typically from 0.5 V to 1.0 V, but is always less than the capacitive threshold of the respective liquid-crystal mixture.

The host mixture used for dielectrically positive and dielectrically neutral compounds is ZLI-4792 and the host mixture used for dielectrically negative compounds is ZLI-2857, both from Merck KGaA, Germany. The change in the dielectric constants of the host mixture after addition of the compound to be investigated and extrapolation to 100% of the compound employed gives the values for the respective compounds to be investigated.

The term threshold voltage usually relates to the optical threshold for 10% relative contrast (V_{10}), unless explicitly stated otherwise.

In relation to the liquid-crystal mixtures of negative dielectric anisotropy, however, the term threshold voltage in the present application is used for the capacitive threshold voltage (V_0), also known as the Freedericksz threshold, unless explicitly stated otherwise.

All concentrations in this application, unless explicitly stated otherwise, are given in per cent by weight and relate to the corresponding mixture or mixture component. All physical properties are and have been determined in accordance with "Merck Liquid Crystals, Physical Properties of Liquid Crystals", status Nov. 1997, Merck KGaA, Germany, and apply to a temperature of 20°C, unless explicitly stated otherwise. Δn is determined at 589 nm and $\Delta\epsilon$ at 1 kHz.

In the case of the liquid-crystal media of negative dielectric anisotropy, the threshold voltage was determined as the capacitive threshold V_0 (also known as the Freedericksz threshold) in test cells produced at Merck KGaA, Germany, with a liquid crystal aligned homeotropically by means of lecithin.

5 The liquid-crystal media according to the invention may, if necessary, also comprise further additives and chiral dopants in the conventional amounts. The amount of these additives employed is in total from 0% to 10%, based on the amount of the mixture as a whole, preferably from 0.1% to 6%. The concentrations of the individual compounds employed is preferably from 0.1% to 3%. The concentration of these and similar additives is not taken into account when indicating the concentrations and the concentration ranges of the liquid-crystal compounds in the liquid-crystal media.

10

The compositions consist of a plurality of compounds, preferably from 3 to 30, particularly preferably from 6 to 20 and very particularly preferably from 10 to 16 compounds, which are mixed in a conventional manner. In general, the desired amount of the components used in smaller amount is dissolved in the components making up the principal constituent, advantageously at elevated temperature. If the selected temperature is above the clearing point of the principal constituent, the completion of the dissolution process is particularly easy to observe. However, it is also possible to prepare the liquid-crystal mixtures in other conventional ways, for example using premixes or from a so-called "multibottle system".

20

By means of suitable additives, the liquid-crystal phases according to the invention can be modified in such a way that they can be employed in any type of ECB, VAN, IPS, GH or ASM-PA LCD display that has been disclosed hitherto.

25

The examples below serve to illustrate the invention without representing a limitation. In the examples, the melting point T (C,N), the transition from the smectic (S) phase to the nematic (N) phase T(S,N) and the clearing point T (N,I) of a liquid-crystal substance are indicated in degrees Celsius.

30

Unless indicated otherwise, all percentages above and below are per cent by weight and physical properties are the values at 20°C, unless explicitly stated otherwise.

35

All the indicated values for temperatures in this application are °C and all temperature differences are correspondingly differential degrees, unless explicitly stated otherwise.

5 In the present application and in the examples below, the structures of the liquid-crystal compounds are indicated by means of acronyms, the transformation into chemical formulae taking place in accordance with Tables A and B below. All radicals C_nH_{2n+1} and C_mH_{2m+1} are straight-chain alkyl radicals having n and m carbon atoms respectively. The coding in Table B is self-evident. In Table A, only the acronym for the parent structure is indicated. In individual cases, the acronym for the parent structure is followed, separated by a hyphen, by a code for the substituents R^1 , R^2 , L^2 and L^2 :

10

15

20












25

30

35

	Code for R ¹ , R ² , L ¹ , L ² , L ³	R ¹	R ²	L ¹	L ²	L ³
5	nm	C _n H _{2n+1}	C _m H _{2m+1}	H	H	H
	nOm	C _n H _{2n+1}	OC _m H _{2m+1}	H	H	H
	nO.m	OC _n H _{2n+1}	C _m H _{2m+1}	H	H	H
	nmFF	C _n H _{2n+1}	C _m H _{2m+1}	H	F	F
	nmOFF	C _n H _{2n+1}	OC _m H _{2m+1}	H	F	F
10	n	C _n H _{2n+1}	CN	H	H	H
	nN.F	C _n H _{2n+1}	CN	F	H	H
	nN.F.F	C _n H _{2n+1}	CN	F	F	H
	nF	C _n H _{2n+1}	F	H	H	H
15	nF.F	C _n H _{2n+1}	F	F	H	H
	nF.F.F	C _n H _{2n+1}	F	F	F	H
	nOF	OC _n H _{2n+1}	F	H	H	H
	nCl	C _n H _{2n+1}	Cl	H	H	H
20	nCl.F	C _n H _{2n+1}	Cl	F	H	H
	nCl.F.F	C _n H _{2n+1}	Cl	F	F	H
	nCF ₃	C _n H _{2n+1}	CF ₃	H	H	H
	nCF ₃ .F	C _n H _{2n+1}	CF ₃	F	H	H
	nCF ₃ .F.F	C _n H _{2n+1}	CF ₃	F	F	H
25	nOCF ₃	C _n H _{2n+1}	OCF ₃	H	H	H
	nOCF ₃ .F	C _n H _{2n+1}	OCF ₃	F	H	H
	nOCF ₃ .F.F	C _n H _{2n+1}	OCF ₃	F	F	H
	nOCF ₂	C _n H _{2n+1}	OCHF ₂	H	H	H
30	nOCF ₂ .F	C _n H _{2n+1}	OCHF ₂	F	H	H
	nOCF ₂ .F.F	C _n H _{2n+1}	OCHF ₂	F	F	H
	nS	C _n H _{2n+1}	NCS	H	H	H
	nS.F	C _n H _{2n+1}	NCS	F	H	H
35	nS.F.F	C _n H _{2n+1}	NCS	F	F	H
	rVsN	C _r H _{2r+1} -CH=CH-C _s H _{2s} -	CN	H	H	H
	rEsN	C _r H _{2r+1} -O-C _s H _{2s} -	CN	H	H	H

Table A

5	 <p>PCH</p>	 <p>EPCH</p>
10	 <p>BCH</p>	 <p>CCP</p>
15	 <p>CECF</p>	 <p>ECCP</p>
20	 <p>BECH</p>	 <p>EBCH</p>
25	 <p>PTP</p>	 <p>CPTP</p>
30		
35	 <p>CEPTP</p>	

























**CCH****PDX****PYP****PYRP****D****ME****HP****CP****EHP****ET**

Table B:


5	 <p>CCZU-n-X (X = F, Cl or OCF₃)</p>	 <p>CDU-n-X (X = F, Cl or OCF₃)</p>
10	 <p>K3-n</p>	 <p>M3-n</p>
15	 <p>G3-n</p>	 <p>T3-n</p>
20	 <p>Inm</p>	
25	 <p>BCH-n.FX (X = F, Cl or OCF₃)</p>	 <p>CGU-n-X (X = F, Cl or OCF₃)</p>
30	 <p>C-nm</p>	
35		

**CB15****C15**


5

**CCN-nm****NCB-nm**



10

**CCEPC-nm**


15

**CCPC-nm**

20

**CH-nm**

25


HD-nm

30


HH-nm

35


OS-nm

**CHE**


5

**BCH-nmF**


10

**CBC-nm(F)**



15

**ECBC-nm**



20

**ECCH-nm****CCH-n1Em**


25

**T-nFX****B-nO.FX**(X = F, Cl or OCF₃)(X = F, Cl or OCF₃)


30

**PGIGI-n-X****GGP-n-X**(X = F, Cl or OCF₃)(X = F, Cl or OCF₃)


35

**CVCC-n-m**

5

**CVCP-n-m**


10

**CVCVC-n-m**


15

**CP-V-N**


20

**CCG-V-F**


25

**CCP-V-n**


30

**CCP-Vn-m**


35

**CPP-V-m**


5

**CPP-nV-m**


10

**CPP-Vn-m**



15

**CC-n-V**


20

**CC-n-Vm**


25

**CC-n-mV****CC-V-V**

30

**CC-V-Vn**


35

**CC-nV-Vm**


5

**CC-V-nV**


10

**CC-Vn-mV**


15

**CC-nV-Vm**


20

**PCH-n(O)mFF**


25


**CCP-n(O)mFF**

30


**CCY-nO-Om**

35


**CCY-VO-(O)m**




5




10




15




20



25




30




35




**CLY-n-(O)m**


5

**CLY-nO-(O)m**


10

**CFY-n-(O)m**


15

**CFY-nO-(O)m**


20

**YY-n-(O)m**


25

**YY-nO-Om**


30

**CQY-n-(O)m**


35

**CCQY-n-(O)m**


5

**CPQIY-n-(O)m**

10

**CQPY-n-(O)m**

15

**PQPY-n-(O)m**

20

Examples

25

The following examples are intended to explain the invention without representing a limitation. Above and below, percentages are per cent by weight. All temperatures are indicated in degrees Celsius. Δn denotes optical anisotropy (589 nm, 20°C), $\Delta \epsilon$ denotes the dielectric anisotropy (1 kHz, 20°C), H.R. denotes the voltage holding ratio (at 100°C, after 5 minutes in the oven, 1 V), and V_0 , the threshold voltage, was determined at 20°C.

30

35

Example 1

	Compound/ abbreviation	Concentration / % by weight	Physical properties
5	CPQIY-3-O2	10.0	$T(N, I) = 105.5 \text{ } ^\circ\text{C}$
	CPQIY-3-O4	10.0	$n_e(20^\circ\text{C}, 589 \text{ nm}) = 1.5822$
	CPQIY-5-O4	10.0	$\Delta n(20^\circ\text{C}, 589 \text{ nm}) = 0.1001$
10	PCH-304FF	9.0	$\varepsilon_\perp(20^\circ\text{C}, 1 \text{ kHz}) = 8.3$
	PCH-504FF	9.0	$\Delta\varepsilon(20^\circ\text{C}, 1 \text{ kHz}) = -4.6$
	CCP-202FF	4.0	$\gamma_1(20^\circ\text{C}) = 271 \text{ mPa}\cdot\text{s}$
	CCP-302FF	6.0	$t_{\text{store}}(-40^\circ\text{C}) > 1000 \text{ h}$
15	CCP-502FF	6.0	$\text{VHR}(5 \text{ min}, 100^\circ\text{C}) = 89 \text{ } \%$
	CCP-21FF	7.0	$V_0(20^\circ\text{C}) = 2.25 \text{ V}$
	CCP-31FF	10.0	
	CCP-V-1	9.0	
20	CC-3-V1	<u>10.0</u>	
	Σ	100.0	

The liquid-crystal medium is introduced into a VA display with TFT addressing. This display is distinguished, in particular, by the fact that it can be employed in a very large temperature range, as required for so-called broad range applications, for example in mobile telephones and in navigation systems.

Example 2

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	CPQIY-3-O2	10.0	$T(N,I)$	= 71.5	°C
	CPQIY-3-O4	6.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5773	
	CPQIY-5-O4	8.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.0947	
10	D-302FF	20.0	$\varepsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 11.7	
	D-502FF	20.0	$\Delta\varepsilon(20^\circ\text{C}, 1\text{ kHz})$	= -7.5	
	PCH-502FF	14.0	$\gamma_1(20^\circ\text{C})$	= 268	mPa·s
	PCH-504FF	11.0	$t_{\text{store}}(-20^\circ\text{C})$	> 1000	h
15	CCP-302FF	5.0	$t_{\text{store}}(-40^\circ\text{C})$	≥ 500	h
	CCP-502FF	<u>6.0</u>	$V_0(20^\circ\text{C})$	= 1.45	V
	Σ	100.0			

20 As in Example 1, the liquid-crystal medium is introduced into a display with TFT addressing, but here into an IPS display. This display is distinguished, in particular, by a very low addressing voltage.

25

30

35

Example 3

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	CPQIY-3-O4	8.0	$T(N,I)$	= 71.0	°C
	CPQIY-5-O4	8.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5788	
	CCQY-5-O2	5.3	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.1007	
10	PCH-304FF	19.0	$\varepsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 8.5	
	PCH-502FF	9.0	$\Delta\varepsilon(20^\circ\text{C}, 1\text{ kHz})$	= -4.4	
	PCH-504FF	14.0	$\gamma_1(20^\circ\text{C})$	= 219	mPa·s
	CCP-302FF	13.7	$k_1(20^\circ\text{C})$	= 11.8	pN
15	BCH-32	8.0	$k_1/k_3(20^\circ\text{C})$	= 1.24	
	CC-5-V	3.0	$t_{\text{store}}(-30^\circ\text{C})$	> 1000	h
	CC-3-V1	8.0	$t_{\text{store}}(-40^\circ\text{C})$	> 1000	h
	PGIGI-3-F	<u>4.0</u>	$V_0(20^\circ\text{C})$	= 1.92	V
20	Σ	100.0			

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing.

25

30

35

Example 4

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	CCQY-5-O2	7.0	$T(N,I)$	= 99.0	°C
	PCH-304FF	12.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5825	
	PCH-502FF	9.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.1003	
10	PCH-504FF	13.0	$\epsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 8.1	
	CCP-302FF	11.0	$\Delta\epsilon(20^\circ\text{C}, 1\text{ kHz})$	= -4.4	
	CCP-502FF	9.0	$\gamma_1(20^\circ\text{C})$	= 266	mPa·s
	CCP-21FF	7.0	$k_1(20^\circ\text{C})$	= 16.7	pN
15	CCP-31FF	11.0	$k_1/k_3(20^\circ\text{C})$	= 1.13	
	BCH-32	8.0	$t_{\text{store}}(-30^\circ\text{C})$	> 1000	h
	CCP-V-1	10.0	$t_{\text{store}}(-40^\circ\text{C})$	≥ 300	h
	CC-3-V1	<u>3.0</u>	$V_0(20^\circ\text{C})$	= 2.21	V
20	Σ	100.0			

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display is distinguished, in particular, by the fact that it can be employed in a very large temperature range, as required for so-called broad range applications, for example in mobile telephones and in navigation systems.

Example 5

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	CPQIY-3-O4	10.0	$T(N,I)$	= 70.5	°C
	CPQIY-5-O4	10.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5785	
	PCH-304FF	17.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.0993	
10	PCH-502FF	9.0	$\varepsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 8.1	
	PCH-504FF	14.0	$\Delta\varepsilon(20^\circ\text{C}, 1\text{ kHz})$	= -4.2	
	CPY-2-O2	7.0	$\gamma_1(20^\circ\text{C})$	= 187	mPa·s
	CPY-3-O2	7.0	$k_1(20^\circ\text{C})$	= 11.5	pN
15	CCP-V-1	12.0	$k_1/k_3(20^\circ\text{C})$	= 1.24	
	CCH-35	5.0	$t_{\text{store}}(-30^\circ\text{C})$	> 1000	h
	CC-3-V1	9.0	$t_{\text{store}}(-40^\circ\text{C})$	≥ 300	h
	Σ	100.0	$V_0(20^\circ\text{C})$	= 1.95	V

20

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing.

25

30

35

Example 6

	Compound/ abbreviation	Concentration / % by weight	Physical properties
5	PQPY-5-O4	14.0	$T(N,I) = 71.0 \text{ } ^\circ\text{C}$
	PCH-304FF	16.0	$n_e(20^\circ\text{C}, 589 \text{ nm}) = 1.5812$
	PCH-502FF	12.0	$\Delta n(20^\circ\text{C}, 589 \text{ nm}) = 0.1023$
10	PCH-504FF	3.0	$\varepsilon_\perp(20^\circ\text{C}, 1 \text{ kHz}) = 6.9$
	CPY-2-O2	7.0	$\Delta\varepsilon(20^\circ\text{C}, 1 \text{ kHz}) = -3.3$
	CPY-3-O2	7.0	$\gamma_1(20^\circ\text{C}) = 108 \text{ mPa}\cdot\text{s}$
	CCP-V-1	4.0	$t_{\text{store}}(-30^\circ\text{C}) > 1000 \text{ h}$
15	BCH-32	7.0	$t_{\text{store}}(-40^\circ\text{C}) > 1000 \text{ h}$
	CCH-35	5.0	$V_0(20^\circ\text{C}) = 2.10 \text{ V}$
	CC-3-V	4.0	
	CC-5-V	11.0	
20	CC-3-V1	<u>10.0</u>	
	Σ	100.0	

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display exhibits, in particular, very short response times.

30

35

Example 7

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	PQPY-5-1	10.0	$T(N,I)$	= 72.0	°C
	PCH-304FF	18.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5890	
	PCH-502FF	12.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.1054	
10	PCH-504FF	4.0	$\epsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 6.9	
	CCP-31FF	6.0	$\Delta\epsilon(20^\circ\text{C}, 1\text{ kHz})$	= -3.3	
	CPY-2-O2	4.0	$\gamma_1(20^\circ\text{C})$	= 112	mPa·s
	CPY-V-O2	10.0	$t_{\text{store}}(-30^\circ\text{C})$	> 1000	h
15	CCP-V-1	7.0	$t_{\text{store}}(-40^\circ\text{C})$	> 1000	h
	CCP-V2-1	3.0	$V_0(20^\circ\text{C})$	= 2.14	V
	BCH-32	6.0			
	CC-3-V	9.0			
20	CC-3-2V	6.0			
	CC-3-V1	5.0			
	Σ	100.0			

25 As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display exhibits, in particular, very short response times.

30

35

Example 8

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	PQPY-5-O2	20.0	$T(N,I)$	= 86.5	°C
	PCH-304FF	14.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5930	
	PCH-502FF	10.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.1109	
10	PCH-504FF	13.0	$\epsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 9.0	
	CCP-302FF	9.0	$\Delta\epsilon(20^\circ\text{C}, 1\text{ kHz})$	= -5.1	
	CCP-502FF	8.0	$\gamma_1(20^\circ\text{C})$	= 239	mPa·s
	CCP-21FF	3.0	$t_{\text{store}}(-20^\circ\text{C})$	> 1000	h
15	CCP-31FF	6.0	$t_{\text{store}}(-30^\circ\text{C})$	≥ 900	h
	BCH-32	6.0	$t_{\text{store}}(-40^\circ\text{C})$	≥ 600	h
	CCP-V-1	7.0	$V_0(20^\circ\text{C})$	= 1.90	V
	CC-3-V1	<u>5.0</u>			
20	Σ	100.0			

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display is distinguished, in particular, by the fact that it can be employed in a large temperature range and a low addressing voltage is required.

Example 9

	Compound/ abbreviation	Concentration / % by weight	Physical properties		
5	CQPY-5-O2	11.0	T(N,I)	= 86.5	°C
	PCH-304FF	13.0	$n_e(20^\circ\text{C}, 589\text{ nm})$	= 1.5971	
	PCH-502FF	12.0	$\Delta n(20^\circ\text{C}, 589\text{ nm})$	= 0.1080	
10	PCH-504FF	16.0	$\varepsilon_\perp(20^\circ\text{C}, 1\text{ kHz})$	= 9.0	
	CCP-302FF	12.0	$\Delta\varepsilon(20^\circ\text{C}, 1\text{ kHz})$	= -5.2	
	CCP-502FF	13.0	$\gamma_1(20^\circ\text{C})$	= 262	mPa·s
	CCP-21FF	8.0	$t_{\text{store}}(-20^\circ\text{C})$	> 1000	h
15	BCH-32	8.0	$t_{\text{store}}(-30^\circ\text{C})$	\geq 800	h
	CCP-V-1	4.0	$t_{\text{store}}(-40^\circ\text{C})$	\geq 500	h
	PGIGI-3-F	<u>3.0</u>	$V_0(20^\circ\text{C})$	= 1.90	V
	Σ	100.0			

20

As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display is distinguished, in particular, by the fact that it can be employed in a large temperature range.

25

30

35

Example 10

	Compound/ abbreviation	Concentration / % by weight	Physical properties
5	CQY-5-O2	12.0	$T(N,I) = 70 \text{ } ^\circ\text{C}$
	PCH-304FF	18.0	$n_e(20^\circ\text{C}, 589 \text{ nm}) = 1.5850$
	PCH-502FF	9.0	$\Delta n(20^\circ\text{C}, 589 \text{ nm}) = 0.1011$
10	CPY-2-O3	13.0	$\epsilon_\perp(20^\circ\text{C}, 1 \text{ kHz}) = 6.9$
	CPY-3-O3	13.0	$\Delta\epsilon(20^\circ\text{C}, 1 \text{ kHz}) = -3.3$
	BCH-32	6.0	$\gamma_1(20^\circ\text{C}) = 115 \text{ mPa}\cdot\text{s}$
	CCP-V-1	2.0	$t_{\text{store}}(-40^\circ\text{C}) > 1000 \text{ h}$
15	CC-5-V	18.0	$V_0(20^\circ\text{C}) = 2.10 \text{ V}$
	CC-3-V1	<u>9.0</u>	
	Σ	100.0	

20 As in Example 1, the liquid-crystal medium is introduced into a VA display with TFT addressing. This display is distinguished, in particular, by very short response times.


25 The liquid-crystal mixtures of Examples 1 and 3 to 10 can also be used with good results in IPS displays.

30


35

Patent Claims

1. Nematic liquid-crystal medium, characterised in that it comprises
a) a dielectrically negative, liquid-crystalline component (component
A) which comprises one or more dielectrically negative com-
pound(s) of the formula I



in which



R^{11} is alkyl having from 1 to 7 carbon atoms, alkoxy having from 1 to 7 carbon atoms or alkenyloxy having from 2 to 7 carbon atoms, preferably having from 2 to 4 carbon atoms,



R^{12} is alkyl or alkoxy having from 1 to 7 carbon atoms or alkenyl, alkenyloxy or alkoxyalkyl having from 2 to 7 carbon atoms,

one of Z^{11} and Z^{12} is OCF_2 or CF_2O , preferably OCF_2 , and the other is a single bond, and

n is 0 or 1, and

- b) a dielectrically negative, liquid-crystalline component (component B), and optionally
- c) a dielectrically neutral, liquid-crystalline component (component C), and optionally
- d) a dielectrically positive, liquid-crystalline component (component D).

2. Liquid-crystal medium, characterised in that it comprises a or component B which comprises one or more compounds selected from the group consisting of the compounds of the formulae II and III




in which


R^{21} is alkyl or alkoxy having from 1 to 7 carbon atoms or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms,

R^{22} is alkyl or alkoxy having from 1 to 7 carbon atoms or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms,

Z^{21} and Z^{22} are each, independently of one another, $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{COO}-$ or a single bond,




and




and


5




and




are each, independently of one another,



10



15

 L^{21} and L^{22}

are both C-F or one of the two is N and the other is C-F, preferably both are C-F,

20

m

is 0 or 1,

 Z^3 is $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{COO}-$ or a single bond,

25

 R^{31} and R^{32}

are each, independently of one another, alkyl or alkoxy having from 1 to 7 carbon atoms, having from 1 to 7 carbon atoms or alkoxyalkyl, alkenyl or alkenyloxy having from 2 to 7 carbon atoms, and

30

l

is 1 or 2.


3. Liquid-crystal medium according to at least one of Claims 1 and 2, characterised in that it comprises one or more compounds of the formula II as given in Claim 2.

35

4. Liquid-crystal medium according to at least one of Claims 1 to 3, characterised in that it comprises one or more compounds of the formula III as given in Claim 2.
5. Liquid-crystal medium according to at least one of Claims 1 to 4, characterised in that it comprises a component C according to Claim 1.
6. Liquid-crystal medium according to at least one of Claims 1 to 5, characterised in that it comprises a component D according to Claim 1.
7. Electro-optical display containing a liquid-crystal medium according to at least one of Claims 1 to 6.
8. Display according to Claim 7, characterised in that it is an active matrix display.
9. Display according to at least one of Claims 7 and 8, characterised in that it is an ECB or IPS display.
10. Use of a liquid-crystal medium according to at least one of Claims 1 to 7 in an electro-optical display.

Abstract

The present invention relates to nematic liquid-crystal media which
a) a dielectrically negative, liquid-crystalline component A comprising one
or more compounds of the formula I



in which the parameters are as defined in the text, and
b) a dielectrically negative, liquid-crystalline component B, and optionally
c) a dielectrically neutral, liquid-crystalline component C, and optionally
d) a dielectrically positive, liquid-crystalline component D,
and to the use of these media in liquid-crystal displays, and to liquid-crystal displays which use these media, in particular VAN and IPS displays.